



DRY MIX JOINT COMPOUND

DARVAN® 7NS
Dispersing Agent

PYRAX® WA
PYROPHYLLITE

DRY MIX JOINT COMPOUND

COMPONENT	WEIGHT %
PYRAX® WA ¹ Pyrophyllite	10.00
MarbleWhite® 195 ²	84.78
Attagel® 50 ³	1.00
Elotex® MP 2100 ⁴	3.75
Bermocoll® M30 ⁴	0.17
Darvan® 7NS ¹ Dispersing Agent	0.15
Agitan® P803 ⁵	0.15
Total	100.00

Mix all components until homogenous. When ready to use, blend dry mix at a 2.7:1 ratio with clean water and mix until uniform and creamy.

PAINT PROPERTIES

% Solids by weight	100
Pigment to binder ratio	25.27:1
Calculated VOC	0 lbs/gal

RAW MATERIAL SUPPLIERS

¹Vanderbilt Minerals, LLC - Norwalk, CT

²Specialty Minerals, Inc - Canaan, CT

³BASF Corporation - Florham Park, NJ

⁴Nouryon Chemicals AG - Sempach, Switzerland

⁵Munzing, LLC - Bloomfield, NJ

TRADEMARKS

DARVAN and **PYRAX** are registered trademarks of Vanderbilt Minerals, LLC.

MARBLEWHITE is a registered trademark of Minerals Technologies Inc.

Bermocoll is a registered trademark of Nouryon Surface Chemistry LLC.

Attagel is a registered trademark of BASF Group.

Elotex is a registered trademark of Nouryon Surface Chemistry LLC.

Agitan is a registered trademark of Munzing Chemie GmbH Corporation.

CONTACT INFORMATION

For samples, product information and/or technical service please contact Vanderbilt Minerals, LLC or the Vanderbilt representative in your area:

Vanderbilt Minerals, LLC

33 Winfield Street, P.O. Box 5150, Norwalk, CT 06856-5150

P: (800) 562-2476 F: (203) 855-1220

www.vanderbiltminerals.com

Registered and pending trademarks appearing printed in bold in these materials are those of Vanderbilt Minerals, LLC. For a complete listing, please visit Trademark Listing. 3/05/2020

Before using, read, understand and comply with the information and precautions in the Safety Data Sheets, label and other product literature. The information presented herein, while not guaranteed, was prepared by technical personnel and, to the best of our knowledge and belief, is true and accurate as of the date hereof. No warranty, representation or guarantee, express or implied, is made regarding accuracy, performance, stability, reliability or use. This information is not intended to be all-inclusive, because the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. The user is responsible for determining the suitability of any material for a specific purpose and for adopting such safety precautions as may be required. Vanderbilt Minerals, LLC does not warrant the results to be obtained in using any material, and disclaims all liability with respect to the use, handling or further processing of any such material. No suggestion for use is intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patent, trademark or copyright or to violate any federal, state or local law or regulation.