

Aerosol Protective Oven Film No. 251

		Wt. %
A	VEEGUM® T Magnesium Aluminum Silicate	2.9
	Water	86.4
B	Ethylene Oxide/Propylene Oxide Copolymer (PLURONIC® F-127 ¹)	4.3
	Dimethicone, 60,000 cs (Xiameter® PMX-200 Silicone Fluid 6,000CS ²)	6.4
C	Preservative	q.s.

Procedure:

Step 1 – Sift the **VEEGUM® T** into an established vortex in the water. Mix at maximum available shear until fully hydrated.

Step 2 – Reduce the mixing speed and add the Part B and C ingredients in order, mixing after each addition until uniform.

RAW MATERIAL SUPPLIERS

¹BASF Performance Chemicals, Mount Olive, NJ

²Dow Corning Corporation, Midland, MI

TRADEMARKS

VEEGUM is a registered trademark of Vanderbilt Minerals, LLC.

Pluronic is a registered trademark of BASF Corporation.

Xiameter is a registered trademark of Dow Corning Corporation.

Rev02/07/2014