

Oxalic Acid Gel No. 466

| | | Wt. % |
|----------|--|--------------|
| A | VAN GEL[®] B Magnesium Aluminum Silicate | 2.5 |
| | VANZAN[®] Xanthan Gum | 0.8 |
| | Water | 53.7 |
| B | Oxalic Acid Dihydrate, 12.5% Aqueous Solution | 40.0 |
| | Polysorbate 40 (TWEEN [®] 40 ¹) | 3.0 |

Procedure:

Step 1 — Blend the **VAN GEL[®] B** and **VANZAN[®]** and sift into an established vortex in the water. Mix at maximum available shear until fully hydrated.

Step 2 — Reduce the mixing speed and add the Part B ingredients in order, mixing after each addition until uniform.

RAW MATERIAL SUPPLIERS¹Croda Inc., Edison, NJ**TRADEMARKS**

Registered and pending trademarks appearing printed in bold in these materials are those of Vanderbilt Minerals, LLC. For a complete listing, please visit http://www.vanderbiltminerals.com/ee_content/Documents/Technical/Trademarks_VM_Web.pdf
TWEEN is a registered trademark of Uniqema Americas LLC.

Rev02/07/2014