

Non-Silicone Furniture Polish No. 579

		Wt.%
A	<b>VAN GEL® B</b> Magnesium Aluminum Silicate	0.50
	<b>VANZAN®</b> Xanthan Gum	0.40
	Water	73.15
B	Beeswax Emulsion (Kahl Emulsion BE 720 <sup>1</sup> )	10.00
	Carnauba Wax Emulsion, 40%	10.00
C	Emulsifying Agent (PLURONIC® L44 <sup>2</sup> )	0.35
	Orange Oil (Tech Grade d-limonene <sup>3</sup> )	5.00
D	Preservative	q.s.

Procedure:

**Step 1** – Blend the **VAN GEL® B** and **VANZAN®** and sift into an established vortex in the water. Mix at maximum available shear until fully hydrated.

**Step 2** – Add the Part B, C and D ingredients in order, mixing after each addition until uniform. Avoid air entrapment.

RAW MATERIAL SUPPLIERS

- <sup>1</sup>DeWolf Chemical, Inc., East Providence, RI
- <sup>2</sup>BASF Performance Chemicals, Mount Olive, NJ
- <sup>3</sup>Florida Chemical, Winter Haven, FL

TRADEMARKS

**VAN GEL** and **VANZAN** are registered trademarks of Vanderbilt Minerals, LLC.  
Pluronic is a registered trademark of BASF Corporation.

Rev11/02/2017