

## Concentrated Phosphoric Acid Gel No. 607

		Wt. %
A	<b>VAN GEL® SX</b> Magnesium Aluminum Silicate	2.5
	Water	62.5
B	Phosphoric Acid, 85%	30.0
	Octoxynol-9 (TRITON® X-100 <sup>1</sup> )	5.0

### Procedure:

**Step 1** – Add the **VAN GEL® SX** slowly to the water agitated at high speed. Mix until fully hydrated.

**Step 2** – Reduce mixing speed and add the Part B ingredients in order, mixing after each addition until uniform. Avoid air entrapment.

### RAW MATERIAL SUPPLIERS

<sup>1</sup>Dow Chemical, Midland, MI

### TRADEMARKS

Registered and pending trademarks appearing printed in bold in these materials are those of Vanderbilt Minerals, LLC. For a complete listing, please visit [http://www.vanderbiltminerals.com/ee\\_content/Documents/Technical/Trademarks\\_VM\\_Web.pdf](http://www.vanderbiltminerals.com/ee_content/Documents/Technical/Trademarks_VM_Web.pdf)  
 TRITON is a registered trademark of Union Carbide Corporation.

Rev02/07/2014