

PROTOTYPE FORMULA

Natural Citrus Furniture Polish No. 608

A	VAN GEL® SX Magnesium Aluminum Silicate Water	Wt.% 2.00 72.65
В	Beeswax Emulsion (BE 720 ¹) Carnauba Wax Emulsion, 40%	10.00 10.00
С	Emulsifying Agent (PLURONIC® L44²) Orange Oil (Tech Grade d-limonene³)	0.35 5.00
D	Preservative	q.s.

Procedure:

Step 1 – Add the VAN GEL® SX slowly to the water agitated at high speed. Mix until fully hydrated.

Step 2 – Slowly add the Part B and Part C ingredients in order, mixing well after each until uniform. Avoid air entrapment.

RAW MATERIAL SUPPLIERS

¹DeWolf Chemical, Inc., East Providence, RI ²BASF Performance Chemicals, Mount Olive, NJ

TRADEMARKS

Registered and pending trademarks appearing printed in bold in these materials are those of Vanderbilt Minerals, LLC. For a complete listing, please visit http://www.vanderbiltminerals.com/ee_content/Documents/Technical/Trademarks_VM_Web.pdf PLURONIC is a registered trademark of BASF Corporation.

Rev02/07/2014

³Florida Chemical, Winter Haven, FL