



DARVAN®

811D

Dispersing Agents for Ceramics and Refractories

TECHNICAL DATA

DARVAN® 811D is a dry powder sodium polyacrylate and sodium polymethacrylate dispersing agent. **DARVAN 811D** can be used in all applications where **DARVAN 811** dispersion is used but where dry powder is a prerequisite. **DARVAN 811D** can be successfully used in low moisture castables and in other refractory products where a dispersing agent in its powdered form is preferred.

TYPICAL PROPERTIES

Composition	Low molecular weight sodium polyacrylate with sodium polymethacrylate
Physical State	Granules
Color	White to cream
Solubility	Soluble in water systems
PH (5% Solution)	6.0 to 9.0
Bulk Density	35 to 40 lb./ft. ³
Active Dispersing Agent	92% minimum
Moisture	8% maximum
Storage	DARVAN® 811D Dispersing Agent is hygroscopic and should be stored in a dry area.

CONTACT INFORMATION

For samples, product information and/or technical service please contact Vanderbilt Minerals, LLC or the Vanderbilt representative in your area:

Vanderbilt Minerals, LLC
33 Winfield Street, P.O. Box 5150
Norwalk, CT 06856-5150
P: (800) 562-2476
F: (203) 855-1220
www.vanderbiltminerals.com

DARVAN is a registered trademark of Vanderbilt Minerals, LLC.

3/24/2022

Before using, read, understand and comply with the information and precautions in the Safety Data Sheets, label and other product literature. The information presented herein, while not guaranteed, was prepared by technical personnel and, to the best of our knowledge and belief, is true and accurate as of the date hereof. No warranty, representation or guarantee, express or implied, is made regarding accuracy, performance, stability, reliability or use. This information is not intended to be all-inclusive, because the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. The user is responsible for determining the suitability of any material for a specific purpose and for adopting such safety precautions as may be required. Vanderbilt Minerals, LLC does not warrant the results to be obtained in using any material, and disclaims all liability with respect to the use, handling or further processing of any such material. No suggestion for use is intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patent, trademark or copyright or to violate any federal, state or local law or regulation.