

Specification

DARVAN® 821A Surfactant

May 29, 2020

Product Code: 14442

Composition: Ammonium polyacrylate **Physical State:** Clear yellow liquid

	SPECIFICATION	TEST METHOD
*pH	7.0 – 7.5	T-19
*Solids (130°C, 0.5 g, 30 min.)	39.5 – 40.5%	T-1128
*Specific Gravity	1.16 – 1.19	T-1129
*Viscosity, Brookfield	25 – 50 cps	T-60

Solubility - Highly soluble in aqueous systems

Re-inspection interval: 2 years

*Certified Property

Uses – Recommended for use in the electronic and specialty ceramic fields where a low soda content is required.

DARVAN is a registered trademark of Vanderbilt Minerals, LLC.

The information presented herein, while not guaranteed, was prepared by technical personnel and, to the best of our knowledge and belief, is true and accurate as of the date hereof. No warranty, representation or guarantee, express or implied, is made regarding accuracy, performance, stability, reliability or use. This information is not intended to be all –inclusive, because the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. The user is responsible for determining the suitability of any material for a specific purpose and for adopting such safety precautions as may be required. Vanderbilt Minerals, LLC does not warrant the results to be obtained in using any material, and disclaims all liability with respect to the use, handling or further processing of any such material. No suggestion for use is intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patent or to violate any federal, state or local law or regulation.