

Specification

PYRAX® RG-140

September 23, 2021

RTV Product Code: 33608

Composition: Pyrophyllite. hydrated aluminum silicate

Physical State: Off-white to gray powder

	<u>Specification</u>	Test Method
*Brightness, Fired	55 minimum	T-898
*Expansion/Shrinkage	+2.5 to -2.0%	T-897
*Fineness, retained on 200 mesh	5-10%	T-957

GENERAL INFORMATION

Typical values not routinely measured or reported on the Certificate of Analysis.

Moisture Content 0.5% maximum

*Certified Property

Uses - A refractory grade pyrophyllite used in insulating firebrick, metal pouring refractories, monolithic refractories, ramming, gunning and castable mixes, as well as kiln car refractories.

PYRAX is a registered trademark of R.T. Vanderbilt Holding Company, Inc. and/or its respective wholly owned subsidiaries.

The information presented herein, while not guaranteed, was prepared by technical personnel and, to the best of our knowledge and belief, is true and accurate as of the date hereof. No warranty, representation or guarantee, express or implied, is made regarding accuracy, performance, stability, reliability or use. This information is not intended to be all —inclusive, because the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. The user is responsible for determining the suitability of any material for a specific purpose and for adopting such safety precautions as may be required. Vanderbilt Minerals, LLC does not warrant the results to be obtained in using any material, and disclaims all liability with respect to the use, handling or further processing of any such material. No suggestion for use is intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patent or to violate any federal, state or local law or regulation.