

PYRAX® RG 200

September 23, 2021

RTV Product Code: **33804**
Composition: Hydrated aluminum silicate, pyrophyllite
Physical State: Gray to buff powder

	<u>Specification</u>	<u>Test Method</u>
*Brightness, Fired	55 minimum	T-898
*Shrinkage	2% maximum	T-897
*Fineness, retained on 200 mesh	1.0% maximum	T-706A

GENERAL INFORMATION

Typical values not routinely measured or reported on the Certificate of Analysis.

Density at 25°C	2.8-2.9 Mg/m ³
Moisture Content	0.5% maximum

*Certified Property

Uses - A Valuable refractory raw material for use in:

- 1) Insulating firebrick,*
- 2) Metal pouring refractories,*
- 3) Alumina-silica monolithic refractories (Ramming, gunning, and castable mixes)*
- 4) Kiln car refractories, and*
- 5) Foundry washes.*

Standard Container – 50 pound paper bag